Product data sheet

2021.05.10

English

950003

Date

SDS

Language

SN100CLe+ (SnNi0.15)



SUMMARY

SN100CLe+ copper-reduced solder with addition of nickel is the replenishment alloy for SN100CL solder to keep the solder bath within the process limits.

ALLOY	SN100CLe+ (SnNi0.15)			
PROCESS				
Leadfree		9		
Leaded		1		
First filling*		1		
Refilling*		9		
	*follow Appl	cation Note		
INDUSTRY APPLICA	TION			
Standard electronics		9		
Industrial electronics		9		
Hi-Rel electronics (automotive)		9		
PROCESS CAPABILITY				
Wave soldering		1		
Selective soldering		1		
Dip soldering		6		
Wire tinning		6		
Process: Ambient		9		
Process: N2 partial		N/A		
Process: N2 vull tunne	el	N/A		
Reduces dross		8		
Reduces bridging		8		
Improves PTH filling		N/A		
Shiny joint appearance	3	9		

Legend		
Especially made for this purpose		
Generally qualified for this purpose		
Generally usable, but not the best choice		
Generally not usable for this purpose	3 - 4	
Wrong choice		

Check material compatibility with every process change.

SN100 SnNi(
SnNi	
SnNi0.15	
not compliant	
-	
[ºC]	227
[ºC]	227
[ºC]	260 - 320
-	- [00] [00]

COMPOSITION					
Tin	[Sn]	Remainder			
Copper	[Cu]	max. 0.2			
Nickel	[Ni]	0.13 - 0.17			
Germanium	[Ge]	0.005 - 0.007			
Silver	[Ag]	max. 0.05			
Aluminium	[AI]	max. 0.001			
Arsenic	[As]	max. 0.03			
Gold	[Au]	max. 0.03			
Bismuth	[Bi]	max. 0.03			
Cadmium	[Cd]	max. 0.002			
Iron	[Fe]	max. 0.02			
Indium	[ln]	max. 0.03			
Lead	[Pb]	max. 0.05			
Antimony	[Sb]	max. 0.05			
Zinc	[Zn]	max. 0.001			

SHAPE AND DIMENSION*					
Ingot	1 kg	LxWxH [mm]	325x28x15		
Ingot with loop	3.7 kg	LxWxH [mm]	540x50/40x20		
	4 kg	LxWxH [mm]	515x50/48x22		
Bar	Rectangle	[mm]	400x10x8		
	Triangular	[mm]	400x10x10		
Pellet		[mm]	12x25		
Solid wire	ø	[mm]	1.0 - 6.0		

*other dimensions on request

Disclaimer:

Read AN before use. Read MSDS before use.

This information is intended as advice to the best of our knowledge. The provided data is based on our own measurements, they do not provide any guaranteed properties nor are these delivery specifications. Due to the versatility of materials, applications and taking in consideration the industrial property rights of third parties, Balver Zinn Josef Jost GmbH & Co. KG cannot take any liability.

BALVER ZINN®