SN100CeS+ (SnNi0.05Ge0.025)

 Date
 2021.05.10

 Language
 English

 SDS
 950002



SUMMARY

SN100CeS+ copper-reduced solder is the replenishment alloy for SN100CS+ solder to keep the solder bath within the process limits.

ALLOY	SN100CeS+ (SnNi0.05Ge0.025)	
PROCESS		
Leadfree		9
Leaded		1
First filling*		1
Refilling*		9

*follow Application Note

INDUSTRY APPLICATION		
Standard electronics	9	
Industrial electronics	9	
Hi-Rel electronics (automotive)	8	

PROCESS CAPABILITY	
Wave soldering	9
Selective soldering	8
Dip soldering	8
Wire tinning	4
Process: Ambient	9
Process: N2 partial	9
Process: N2 vull tunnel	8
Reduces dross	10
Reduces bridging	10
Improves PTH filling	10
Shiny joint appearance	10

Legend		
Especially made for this purpose	9 - 10	
Generally qualified for this purpose		
Generally usable, but not the best choice		
Generally not usable for this purpose		
Wrong choice		

Check material compatibility with every process change.

Read AN before use.

Read MSDS before use.

PROPERTIES			
Manufacturing standard	WBZ.:	WBZ.: Triple X	
Alloy Code	SN10	SN100CeS+	
Alloy composition	SnNi0.0	SnNi0.05Ge0.025	
ANSI/J-STD-006C: 2013	not co	not compliant	
DIN EN ISO 9453:2021-01		-	
Liquidus	[°C]	227	
Solidus	[°C]	227	
Recommended working range*	[°C]	260 - 320	

*follow Application Note

COMPOSITION	
Tin	[Sn] Remainder
Copper	[Cu] max. 0.2
Nickel	[Ni] 0.04 - 0.06
Germanium	[Ge] 0.02 - 0.03
Silver	[Ag] max. 0.05
Aluminium	[AI] max. 0.001
Arsenic	[As] max. 0.03
Gold	[Au] max. 0.03
Bismuth	[Bi] max. 0.03
Cadmium	[Cd] max. 0.002
Iron	[Fe] max. 0.02
Indium	[ln] max. 0.03
Lead	[Pb] max. 0.05
Antimony	[Sb] max. 0.05
Zinc	[Zn] max. 0.001

SHAPE AND DIMENSION*			
Ingot	1 kg	LxWxH [mm]	325x28x15
Ingot with loop	3.7 kg	LxWxH [mm]	540x50/40x20
	4 kg	LxWxH [mm]	515x50/48x22
Bar	Rectangle	[mm]	400x10x8
	Triangular	[mm]	400x10x10
Pellet		[mm]	12x25
Solid wire	0	[mm]	1.0 - 6.0
*ather dimensions on request			

*other dimensions on request

Disclaimer:

This information is intended as advice to the best of our knowledge. The provided data is based on our own measurements, they do not provide any guaranteed properties nor are these delivery specifications. Due to the versatility of materials, applications and taking in consideration the industrial property rights of third parties, Balver Zinn Josef Jost GmbH & Co. KG cannot take any liability.

2011 24 5