

Zn99.995-Optilooop[®]

Rev: 21.11

Date 2025.09.01
Language English
SDS 950051



SUMMARY

Optilooop[®] is characterised by particularly efficient and uniform dissolution and is excellently suited for use with titanium baskets
Soluble zinc anodes made of particularly pure SHG Special High Grade Zinc according to EN 1179 (Z1).
When using titanium baskets, the Optilooop[®] is outstandingly suitable.

ALLOY	Zn99.995-Optilooop [®]
PROCESS	
corrosion protection	9
Wear Protection	1
INDUSTRY APPLICATION	
Soluble anode	9
Insoluble anode	1

PROCESS CAPABILITY	
Flame spraying	1
Arc Spraying	1
Plain Bearing Process	1
Capacitor contacting	1
Electroplating	9
Dissolution Behaviour	9
Cast / Cast-in suspension	1
Soldered suspension (copper)	1

Legend	
<i>Especially made for this purpose</i>	9 - 10
<i>Generally qualified for this purpose</i>	7 - 8
<i>Generally usable, but not the best choice</i>	5 - 6
<i>Generally not usable for this purpose</i>	3 - 4
<i>Wrong choice</i>	1 - 2

PROPERTIES	
Manufacturing standard	EN 1179: 2003 (Z1)
Alloy Code	Optilooop [®]
Alloy composition	Zn99.995

COMPOSITION		
Zinc	[Zn]	99.995
Lead	[Pb]	max. 0.003
Cadmium	[Cd]	max. 0.005
Iron	[Fe]	max. 0.002
Tin	[Sn]	max. 0.001
Copper	[Cu]	max. 0.001
Aluminum	[Al]	max. 0.001

DELIVERY FORM		
Optilooop [®]	ØxH [mm]	Ø 41-50 x 25

Check material compatibility with every process change!

Read AN before use.

Read MSDS before use.

Disclaimer:

This information is intended as advice to the best of our knowledge. The provided data is based on our own measurements, they do not provide any guaranteed properties nor are these delivery specifications. Due to the versatility of materials, applications and taking in consideration the industrial property rights of third parties, Balver Zinn Josef Jost GmbH & Co. KG cannot take any liability.