

**Date** 2021.08.18  
**Language** English  
**SDS** 950410



**Summary**

396-DRX-M+ is an ORL0 classified, water-based flux for wave soldering. It is based on organic acids and leaves hardly any visible residue. The 396-DRX-M+ prevents bridging.

Flux code	396-DRX-M+
<b>PROCESS</b>	
No-Clean process	9
Post-solder cleaning	8

<b>INDUSTRY APPLICATION</b>	
Standard electronics	8
Industrial electronics	9
Hi-Rel electronics (automotive)	4

<b>PROCESS CAPABILITY</b>	
Foam fluxing	4
Spray fluxing	9
Short preheat	6
Short contact time	9
Pb-free process Air	9
Pb-free process N2 wave	9
Pb-free process N2 Tunnel	8
Skipped joints	9
Solderballing	8
Bridging	9
Promotes wicking	9
PTH filling	9
Cosmetic cleanliness	8
Cosmetic cleanliness N2	9
Shiny joint appearance	8
Pin testability	9
Conformal coating (see AN)	TBD

<b>Legend</b>	
<i>Especially made for this purpose</i>	9 - 10
<i>Generally qualified for this purpose</i>	7 - 8
<i>Generally usable, but not the best choice</i>	5 - 6
<i>Generally not usable for this purpose</i>	3 - 4
<i>Wrong choice</i>	1 - 2

<b>CLASSIFICATION</b>	
DIN EN ISO 9454-1: 2016	2131
IPC-J-STD-004-A: 2004	ORL0

<b>PROPERTIES</b>		
Density	@20°C [kg/dm³]	1.008
Solid content	[% w/w]	3.4
Acid number	[mg KOH/g]	27.7
Water content	[% w/w]	96
VOC content	[% w/w]	Remainder
Filmformer(s)		Organic
Color		Colorless
Odor		none
Flashpoint COC	[°C]	None
Thinners		Di-water

<b>TEST REPORTS</b>			
Certificate of Compliance		Website	
Application Note		EN/DE	
Copper Mirror	IPC-TM-650 2.3.32		Pass
Halides	IPC-TM-650 2.3.33	[Silver Chromate]	Pass
Halide	IPC-TM-650 2.3.35.1	[Fluoride by Spot]	Pass
Copper Corrosion	IPC-TM-650 2.6.15		Pass
SIR	IPC-TM-650 2.6.3.3		Pass
ECM	IPC-TM-650 2.6.14.1		N/A

<b>PACKAGING AND STORAGE</b>		
Packaging can	(HDPE) [liter]	10
Packaging Drum	(HDPE) [liter]	200
Shelf-life in months		
Storage temperature	20-25 °C	24

**Check material compatibility with every process change!**  
**Industrial chemical product.**  
**Read SDS before use.**

**Disclaimer:**  
 The information given in this publication has been worked up to the best of the knowledge of Cobar as well as taking into consideration the applicable laws and regulations. We cannot anticipate all conditions under which this information and our products or the products of other manufacturers in combination with our products may be used. We accept no responsibility for results obtained by the application of this information or the safety and suitability of our products alone or in combination with other products. Users are advised to make their own tests to determine the safety and suitability of each such product or product combination for their own purposes. Unless otherwise agreed in writing, we sell the products without warranty, and buyers and users assume all responsibility and liability for loss or damage arising from the handling and use of our products, whether used alone or in combination with other products.