

SN96C-LF2220NC

Rev: 04.9

Date 2021.11.15
 Language EN
 SDS 950202



SUMMARY

The RELO classified, halide-free, no-clean solder wire LF2220NC has been specially developed for lead-free repair and rework soldering.

| Solder Wire | SN96C-LF2220NC |
|----------------------|----------------|
| PROCESS | |
| No-Clean process | 9 |
| Post-solder cleaning | 8 |
| Water soluble | 1 |

| INDUSTRY APPLICATION | |
|---------------------------------|---|
| Standard electronics | 6 |
| Industrial electronics | 8 |
| Hi-Rel electronics (automotive) | 9 |

| PROCESS CAPABILITY | |
|------------------------|---|
| Manual soldering | 9 |
| Robot soldering | 9 |
| Laser soldering | 7 |
| Wetting properties | 9 |
| Wetting time | 9 |
| Solderball formation | 7 |
| Flux spattering | 7 |
| Smoke formation | 8 |
| Tip lifetime | 8 |
| Shiny joint appearance | 7 |
| Cosmetic cleanliness | 9 |
| ICCT compatible | 9 |
| Conformal coating | 7 |

| Legend | |
|--|--------|
| <i>Especially made for this purpose</i> | 9 - 10 |
| <i>Generally qualified for this purpose</i> | 7 - 8 |
| <i>Generally usable, but not the best choice</i> | 5 - 6 |
| <i>Generally not usable for this purpose</i> | 3 - 4 |
| <i>Wrong choice</i> | 1 - 2 |

Check material compatibility with every process change!

Industrial chemical product.

Read MSDS before use.

Disclaimer:

The information given in this publication has been worked up to the best of the knowledge of Cobar as well as taking into consideration the applicable laws and regulations. We cannot anticipate all conditions under which this information and our products or the products of other manufacturers in combination with our products may be used. We accept no responsibility for results obtained by the application of this information or the safety and suitability of our products alone or in combination with other products. Users are advised to make their own tests to determine the safety and suitability of each such product or product combination for their own purposes. Unless otherwise agreed in writing, we sell the products without warranty, and buyers and users assume all responsibility and liability for loss or damage arising from the handling and use of our products, whether used alone or in combination with other products.

| CLASSIFICATION | |
|-------------------------|------|
| DIN-EN-ISO-9454-1: 2016 | 1222 |
| IPC-J-STD-004-A: 2004 | RELO |

| PROPERTIES | | |
|-----------------------------|--------------|-----------|
| Flux code | 2220 | |
| Alloy code | SN96C | |
| Alloy composition | SnAg3.8Cu0.7 | |
| Liquidus | [°C] | 217 |
| Solidus | [°C] | 217 |
| Recommended soldering temp. | [°C] | 320 - 370 |
| Acid number | [mg KOH/g] | 220 |
| Flux content | [% w/w] | 2.2 |
| Residues | Colorless | |

| TEST REPORTS | | | |
|---------------------------|---------------------|--------------------|-----------|
| Certificate of Compliance | | | Website |
| RoHS Compliant | | | Available |
| Application Note | | | EN/DE |
| Copper Mirror | IPC-TM-650 2.3.32 | | Pass |
| Halides | IPC-TM-650 2.3.33 | [Silver Chromate] | Pass |
| Halide | IPC-TM-650 2.3.35.1 | [Fluoride by Spot] | Pass |
| Copper Corrosion | IPC-TM-650 2.6.15 | | Pass |
| SIR | IPC-TM-650 2.6.3.3 | | Pass |
| ECM | IPC-TM-650 2.6.14.1 | | Pass |

| PACKAGING AND STORAGE | | | |
|------------------------------|------------|-----------|-----------|
| Reels | | | |
| Label | 63/37 | BZ | K80 |
| Weight [kg] | 0.25 / 0.4 | 0.5 / 1.0 | 0.4 / 0.8 |
| Height [mm] | 63 | 80 | 80 |
| External diameter [mm] | 63 | 76 | 80 |
| Internal diameter [mm] | 11 | 30 | 16 |
| Reels per carton | 10 | 10 | 10 |
| Standard wire diameter [mm] | | | 0.3 - 3.5 |
| Minimum shelf-life in months | 4-10 °C | | 60 |