Product data sheet

BALVER ZINN®

Sn63Pb37-3135NC

 Date
 2021.10.28

 Language
 English

 SDS
 950203





SUMMARY

The REM1 classified, halide-containing, no-clean 3135NC solder wire is suitable for all soldering tasks with lead-containing solders where halide activators are permitted.

Solder Wire	Sn63Pb37-3135NC	
PROCESS		
No-Clean process		9
Post-solder cleaning		8
Water soluble		1

INDUSTRY APPLICATION		
Standard electronics	9	
Industrial electronics		
Hi-Rel electronics (automotive)		

PROCESS CAPABILITY	
Manual soldering	9
Robot soldering	9
Laser soldering	8
Wetting properties	9
Wetting time	9
Solderball formation	9
Flux spattering	9
Smoke formation	9
Tip lifetime	9
Shiny joint appearance	9
Cosmetic cleanliness	9
ICCT compatible	9
Conformal coating	7

Legend		
Especially made for this purpose	9 - 10	
Generally qualified for this purpose		
Generally usable, but not the best choice		
Generally not usable for this purpose		
Wrong choice	1 - 2	

Check material compatibility with every process change!

Industrial chemical product.

Read MSDS before use.

Product contains SVHC substance Lead with more than 0,1 Mass%.

CLASSIFICATION		
1223		
REM1		

PROPERTIES			
Flux code	3135		
Alloy code	Sn63Pb37		
Alloy composition	Sn63Pb37		
Liquidus	[°C]	183	
Solidus	[°C]	183	
Recommended soldering temp.	[°C]	280 - 330	
Acid number	[mg KOH/g]	220	
Flux content	[% w/w]	2.2	
Residues		Colorless	

TEST REPORTS			
Certificate of Compliance		Website	
Declaration of Conformity 2011/65/EU (RoHS)		No	
Application Note		EN/DE	
Copper Mirror	IPC-TM-650 2.3.32		М
Halides	IPC-TM-650 2.3.33	[Silver Chromate]	Fail
Halide	IPC-TM-650 2.3.35.1	[Fluoride by Spot]	Pass
Copper Corrosion	IPC-TM-650 2.6.15		Pass
SIR	IPC-TM-650 2.6.3.3		Pass
ECM	IPC-TM-650 2.6.14.1		N/A

PACKAGING AND STORAGE		
Reels		
Label	K63	BZ
Weight [kg]	0.4	0.25 / 0.5 / 1.0
Height [mm]	63	80
External diameter [mm]	63	76
Internal diameter [mm]	11	30
Reels per carton	10	10
Standard wire diameter [mm]	0	0.3 - 3.5
Minimum shelf-life in months	20-25 °C	60

Disclaimer:

This information is intended as advice to the best of our knowledge. The provided data is based on our own measurements, they do not provide any guaranteed properties nor are these delivery specifications. Due to the versatility of materials, applications and taking in consideration the industrial property rights of third parties, Balver Zinn Josef Jost GmbH & Co. KG cannot take any liability.