

SN100CeS+ (SnNi0.05Ge0.025)

Rev: 21.5

Date 2021.05.10
Language English
SDS 950002



SUMMARY

SN100CeS+ copper-reduced solder is the replenishment alloy for SN100CS+ solder to keep the solder bath within the process limits.

ALLOY	SN100CeS+ (SnNi0.05Ge0.025)
PROCESS	
Leadfree	9
Leaded	1
First filling*	1
Refilling*	9

*follow Application Note

INDUSTRY APPLICATION	
Standard electronics	9
Industrial electronics	9
Hi-Rel electronics (automotive)	8

PROCESS CAPABILITY	
Wave soldering	9
Selective soldering	8
Dip soldering	8
Wire tinning	4
Process: Ambient	9
Process: N2 partial	9
Process: N2	8
Reduces dross	10
Reduces bridging	10
Improves PTH filling	10
Shiny joint appearance	10

Legend	
<i>Especially made for this purpose</i>	9 - 10
<i>Generally qualified for this purpose</i>	7 - 8
<i>Generally usable, but not the best choice</i>	5 - 6
<i>Generally not usable for this purpose</i>	3 - 4
<i>Wrong choice</i>	1 - 2

Check material compatibility with every process change.

Read AN before use.

Read MSDS before use.

Disclaimer:

The information given in this publication has been worked up to the best of the knowledge of Cobar as well as taking into consideration the applicable laws and regulations. We cannot anticipate all conditions under which this information and our products or the products of other manufacturers in combination with our products may be used. We accept no responsibility for results obtained by the application of this information or the safety and suitability of our products alone or in combination with other products. Users are advised to make their own tests to determine the safety and suitability of each such product or product combination for their own purposes. Unless otherwise agreed in writing, we sell the products without warranty, and buyers and users assume all responsibility and liability for loss or damage arising from the handling and use of our products, whether used alone or in combination with other products.

PROPERTIES		
Manufacturing standard	WBZ.: Triple X	
Alloy Code	SN100CeS+	
Alloy composition	SnNi0.05Ge0.025	
ANSI/J-STD-006C: 2013	not compliant	
DIN EN ISO 9453:2021-01	-	
Liquidus	[°C]	227
Solidus	[°C]	227
Recommended working range*	[°C]	260 - 320

*follow Application Note

COMPOSITION		
Tin	[Sn]	Remainder
Copper	[Cu]	max. 0.2
Nickel	[Ni]	0.04 - 0.06
Germanium	[Ge]	0.02 - 0.03
Silver	[Ag]	max. 0.05
Aluminium	[Al]	max. 0.001
Arsenic	[As]	max. 0.03
Gold	[Au]	max. 0.03
Bismuth	[Bi]	max. 0.03
Cadmium	[Cd]	max. 0.002
Iron	[Fe]	max. 0.02
Indium	[In]	max. 0.03
Lead	[Pb]	max. 0.05
Antimony	[Sb]	max. 0.05
Zinc	[Zn]	max. 0.001

SHAPE AND DIMENSION*			
Ingot	1 kg	LxWxH [mm]	325x28x15
	3.7 kg	LxWxH [mm]	540x50/40x20
Ingot with loop	4 kg	LxWxH [mm]	515x50/48x22
	Bar	Rectangle	[mm]
Triangular		[mm]	400x10x10
Pellet		[mm]	12x25
Solid wire	ø	[mm]	1.0 - 6.0

*other dimensions on request