

## SN96C (SAC387)

Rev: 21.5

Date	2021.05.10
Language	English
SDS	950005



## SUMMARY

Alloy SN96C is a standard eutectic alloy when very high reliability is required.

ALLOY	SN96C (SAC387)
<b>PROCESS</b>	
Leadfree	9
Leaded	1
First filling*	9
Refilling*	8

\*follow Application Note

INDUSTRY APPLICATION	
Standard electronics	6
Industrial electronics	8
Hi-Rel electronics (automotive)	9

PROCESS CAPABILITY	
Wave soldering	9
Selective soldering	8
Dip soldering	6
Wire tinning	1
Process: Ambient	8
Process: N2 partial	8
Process: N2	9
Reduces dross	7
Reduces bridging	8
Improves PTH filling	9
Shiny joint appearance	9

Legend	
<i>Especially made for this purpose</i>	9 - 10
<i>Generally qualified for this purpose</i>	7 - 8
<i>Generally usable, but not the best choice</i>	5 - 6
<i>Generally not usable for this purpose</i>	3 - 4
<i>Wrong choice</i>	1 - 2

Check material compatibility with every process change.

Read AN before use.

Read MSDS before use.

## Disclaimer:

The information given in this publication has been worked up to the best of the knowledge of Cobar as well as taking into consideration the applicable laws and regulations. We cannot anticipate all conditions under which this information and our products or the products of other manufacturers in combination with our products may be used. We accept no responsibility for results obtained by the application of this information or the safety and suitability of our products alone or in combination with other products. Users are advised to make their own tests to determine the safety and suitability of each such product or product combination for their own purposes. Unless otherwise agreed in writing, we sell the products without warranty, and buyers and users assume all responsibility and liability for loss or damage arising from the handling and use of our products, whether used alone or in combination with other products.

## PROPERTIES

Manufacturing standard	WBZ.: Triple X	
Alloy Code	SN96C	
Alloy composition	SnAg3.8Cu0.7	
ANSI/J-STD-006C: 2013	compliant	
DIN EN ISO 9453:2021-01	Alloy 713	
Liquidus	[°C]	217
Solidus	[°C]	217
Recommended working range*	[°C]	260 - 320

\*follow Application Note

## COMPOSITION

Tin	[Sn]	Remainder
Silver	[Ag]	3.6 - 4.0
Copper	[Cu]	0.5 - 0.9
Nickel	[Ni]	max. 0.01
Germanium	[Ge]	-
Aluminium	[Al]	max. 0.001
Arsenic	[As]	max. 0.03
Gold	[Au]	max. 0.03
Bismuth	[Bi]	max. 0.03
Cadmium	[Cd]	max. 0.002
Iron	[Fe]	max. 0.02
Indium	[In]	max. 0.03
Lead	[Pb]	max. 0.05
Antimony	[Sb]	max. 0.05
Zinc	[Zn]	max. 0.001

## SHAPE AND DIMENSION\*

Ingot	1 kg	LxWxH [mm]	325x28x15
Ingot with loop	3.7 kg	LxWxH [mm]	540x50/40x20
	4 kg	LxWxH [mm]	515x50/48x22
Bar	Rectangle	[mm]	400x10x8
	Triangular	[mm]	400x10x10
Pellet		[mm]	12x25
Solid wire	ø	[mm]	1.0 - 6.0

\*other dimensions on request