Sn99.7Ag0.3

 Date
 2025.08.26

 Language
 English

 SDS
 950010



## SUMMARY

Sn99.7Ag0.3 copper-reduced solder is the replenishment alloy for SCA0703 solder to keep the solder bath within the process limits.

ALLOY	Sn99.7Ag0.3	
PROCESS		
Leadfree		9
Leaded		1
First filling*		1
Refilling*		9

\*follow Application Note

INDUSTRY APPLICATION	
Standard electronics	9
Industrial electronics	8
Hi-Rel electronics (automotive)	6

PROCESS CAPABILITY		
Wave soldering	9	
Selective soldering	8	
Dip soldering	8	
Wire tinning	4	
Process: Ambient	8	
Process: N2 partial	8	
Process: N2 vull tunnel	9	
Reduces dross	7	
Reduces bridging	8	
Improves PTH filling	8	
Shiny joint appearance	6	

Legend		
Especially made for this purpose	9 - 10	
Generally qualified for this purpose	7 - 8	
Generally usable, but not the best choice	5 - 6	
Generally not usable for this purpose		
Wrong choice	1 - 2	

Check material compatibility with every process change.

Read AN before use.

Read MSDS before use.

PROPERTIES			
Manufacturing standard	WBZ.	WBZ.: Triple X	
Alloy Code	Sn99	Sn99.7Ag0.3	
Alloy composition	Sn99.7Ag0.3		
ANSI/J-STD-006C: 2013	con	compliant	
DIN EN ISO 9453:2021-01	-		
Liquidus	[°C]	228	
Solidus	[°C]	217	
Recommended working range*	[°C]	260 - 320	

\*follow Application Note

COMPOSITION			
Tin	[Sn]	Remainder	
Silver	[Ag]	0.2 - 0.4	
Copper	[Cu]	max. 0.05	
Nickel	[Ni]	max. 0.01	
Germanium	[Ge]	-	
Aluminium	[AI]	max. 0.001	
Arsenic	[As]	max. 0.03	
Gold	[Au]	max. 0.03	
Bismuth	[Bi]	max. 0.03	
Cadmium	[Cd]	max. 0.002	
Iron	[Fe]	max. 0.02	
Indium	[ln]	max. 0.03	
Lead	[Pb]	max. 0.05	
Antimony	[Sb]	max. 0.05	
Zinc	[Zn]	max. 0.001	

SHAPE AND DIMENSION*			
Ingot	1 kg	LxWxH [mm]	325x28x15
Ingot with loop	3.7 kg	LxWxH [mm]	540x50/40x20
	4 kg	LxWxH [mm]	515x50/48x22
Bar	Rectangle	[mm]	•
	Triangular	[mm]	400x10x10
Pellet		[mm]	12x25
Solid wire	0	[mm]	1.0 - 6.0

\*other dimensions on request

## Disclaimer:

This information is intended as advice to the best of our knowledge. The provided data is based on our own measurements, they do not provide any guaranteed properties nor are these delivery specifications. Due to the versatility of materials, applications and taking in consideration the industrial property rights of third parties, Balver Zinn Josef Jost GmbH & Co. KG cannot take any liability.

Rev: 21 5