

**Product** 95-RXZ-M  
**Date** 2018.04.13  
**Release** 14.1  
**Language** English

## General wave soldering flux

### Summary

Low-VOC -- General wave flux -- Anti solder balling -- Can be used in various applications

FLUX CODE	95-RXZ-M
<b>PROCESS</b>	
No-Clean process	5
Post-solder cleaning	3
<b>INDUSTRY APPLICATION</b>	
Consumer electronics	3
Standard industrial electronics	5
Hi-Rel electronics (automotive)	4
<b>PROCESS CAPABILITY</b>	
Foam fluxing	5
Spray fluxing	5
Short preheat	4
Short contact time	5
Pb-free process Air	4
Pb-free process N2 wave	5
Pb-free process N2 Tunnel	5
Skipped joints	5
Solderballing	5
Bridging	5
PTH filling	5
Cosmetic cleanliness	3
Cosmetic cleanliness N2	4
Shiny joint appearance	4
Pin testability	5
Conformal coating (see AN)	3

Legend	
<i>Especially made for this purpose</i>	5
<i>Generally qualified for this purpose</i>	4
<i>Generally usable, but not the best choice</i>	3
<i>Generally not usable for this purpose</i>	2
<i>Wrong choice</i>	1

CLASSIFICATION	
DIN EN 29454-1: 1994	1.2.3.A
IPC-J-STD-004-A: 2004	RELO

PROPERTIES			
Density		@20°C [kg/dm³]	0.9
Acid number	IPC-TM-650 2.3.13	[mg KOH/g]	15.9
Solid content	IPC-TM-650 2.3.34	[% w/w]	1.8
Water content		[% w/w]	40
VOC content		[% w/w]	Remainder
Color			Colorless
Odor			Mild Alcoholic
Thinners			308-00

TEST REPORTS			
Certificate of Compliance			Website
Application Note			EN/DE
Copper Mirror	IPC-TM-650 2.3.32		L
Halides	IPC-TM-650 2.3.33	[Silver Chromate]	Pass
Halide	IPC-TM-650 2.3.35.1	[Fluoride by Spot]	Pass
Copper Corrosion	IPC-TM-650 2.6.15		L
SIR	IPC-TM-650 2.6.3.3		Pass

PACKAGING AND STORAGE		
Packaging can	(HDPE) [liter]	10
Packaging Drum	(HDPE) [liter]	200
<b>Shelf-life in months</b>		
Storage temperature	20-25 °C	12

Check material compatibility with every process change!

Industrial chemical product.

Read SDS before use.

#### Disclaimer:

The information given in this publication has been worked up to the best of the knowledge of Cobar as well as taking into consideration the applicable laws and regulations. We cannot anticipate all conditions under which this information and our products or the products of other manufacturers in combination with our products may be used. We accept no responsibility for results obtained by the application of this information or the safety and suitability of our products alone or in combination with other products. Users are advised to make their own tests to determine the safety and suitability of each such product or product combination for their own purposes. Unless otherwise agreed in writing, we sell the products without warranty, and buyers and users assume all responsibility and liability for loss or damage arising from the handling and use of our products, whether used alone or in combination with other products.